

DESCRIPTION

Urethane 2Pack™ is an aliphatic (non-yellowing), high solid, two pack, high performance polyurethane coating designed for use where outstanding resistance to weathering, chemicals, and excellent gloss retention is required. Urethane 2Pack™ coating provides an extremely tough but flexible, hard wearing film and is used as a protective coating for high traffic areas. It is perfect for use in a wide range of environments where a lasting solution to floor maintenance problems is essential. The exceptional resistance to a wide variety of chemical spillage and fumes makes this product ideal for use in high traffic commercial environments. The products unique feature and benefits is water & chemical resistant, excellent adhesion, high corrosion resistance, high durability, joint less, easy and fast to apply, and easy to clean and maintain. Even tough Urethane 2Pack is chemical resistant to most chemicals, we still recommend that any chemical spills should be cleaned up immediately. Can be used interior and exterior.

FEATURES & ADVANTAGES

- Non-yellowing
- Excellent adhesion/inter-coat adhesion
- Extreme abrasion resistance
- Good water & chemical resistance
- High durability
- Perfect for heavy-duty environments
- Retards growth of mould, fungus, mildew and bacteria
- Excellent wear and scratch resistance
- For interior & exterior use
- Easy to apply, clean & maintain

RECOMMENDED USE

- Decorative finishes
- High traffic areas
- Hallways, Corridors & Hospitals
- Polished or hooned concrete
- Garages and workshops
- Sealing concrete and drive ways
- Factories and shops
- Industrial, domestic and retail flooring
- Top Coat for epoxies and flake flooring
- Restaurants & Public Municipalities
- Schools, Showrooms & much more...

TECHINICAL DATA & CHARACTERISTICS

APPEARANCE	Liquid
COLOUR	Clear
VOLUME SOLIDS	44 - 48 %
FINISH	Gloss, Satin or Matt
COVERAGE	8 – 12m ²
MIX RATIO	3 : 1 (3 Parts A to 1 Part B)
PACK SIZES	20L Kit / 15L Urethane Part A, 5L Hardener Part B
SPECIFIC GRAVITY	Part A 0.97 – 0.99 kg/l Part B 0.95 – 0.97 kg/l
POT LIFE	35 – 60 minutes
DRYING TIME	2 – 6 hours @ 25°C
RECOAT TIME	4 – 24 hours @ 25°C
FULL CURE	7 days @ 25°C
SHELF LIFE	12 months, if properly stored in original unopened containers at temperatures between 10° C and 30°C, away from sunlight.

* The pot life time depends on climatic conditions and temperatures.

** Drying times generally depend on air circulation, temperature, film thickness, and application methods. The figures given above are typical with good ventilation, typical film thickness and single coat application.

SURFACE PREPERATION

All surface preparation has to be carried out to Australian Standard or International Standard. New concrete must be cured for a minimum of 28 days before a coating.

Concrete moisture test should be carried out prior coating application as per Standard ASTM4263 and/ or International Standard. The moisture content should be less than 4%.

Surface to be treated must be structurally sound and the substrate compressive strength should be at least 25MPa. All non-structural cracks, holes and surface deformities should be repaired.

In general, the surface to be treated **MUST** be clean and free of all traces of loose material, dirt, debris, mildew, oil, grease, old coatings, curing compounds, release agents, laitance, dust and other contaminants.

All new or old concrete surfaces should be prepared by mechanical grinding, abrasive blasting, blast-tracking, or any other suitable preparation/cleaning methods. Check if all traces of oil and other contaminations has been completely removed. Sprinkle a few water drops over the surface, if all water is quickly absorbed, the surface is sufficiently oil and grease free. If the water beads up, even in certain areas only, further preparation/cleaning has to be carried out.

For more detailed information, see following standard codes of practice, guides and techniques:

ASTM D4258 Standard practice for surface cleaning concrete for coating

ASTM D4259 Practice for abrading concrete

ASTM D4260 Practice for liquid and gelled acid etching of concrete

ASTM D4262 Test method for pH of chemically cleaned or etched concrete surfaces

ASTM D4263 Test method indicating moisture in concrete by the plastic sheet method

ASTM D4285 Test method for indicating oil or water compresses air

APPLICATION & GUIDELINES

Mixing Gloss, Satin or Matt Versions

Mix Urethane 2Pack™ (3 Parts A) with Urethane 2Pack™ Hardener (1 Part B). The mix ratio is 3:1. Always add Part B into Part A and make sure you add Part B slowly while mixing Part A. Use a mechanical mixer to ensure thorough mixing and avoid aeration when mixing the product. Use a lint free epoxy roller to apply the product. Always mix full pack sizes to avoid incorrect measure of ratio. When using the Urethane 2Pack™ Matt or Satin version, ensure the material in the bucket is regularly stirred during the application process to avoid the matting agent settling on the bottom of the bucket. If not observed, coating differences might occur.

Tint Packs

Shake or stir tint pack well before use. Check colour prior mixing with Urethane 2Pack™. Pour only as much Urethane 2Pack™ as needed in a separate bucket. Measure correct tint pack ratio appropriate to your amount of Urethane 2Pack™ to be used. Mix ratio is 1L APU Colour Tint Pack™ to 20L Urethane 2Pack™. Add tint pack into the urethane. Use a mechanical mixer to distribute the pigments properly and ensure thorough mixing and avoid aeration when mixing the product.

Application

Priming is recommended before the first coat to prevent pin holing and to minimise sink-back of material. Check colour prior to application, if you are using a tinted version. Prime coat with approximately 8-12m²/L, check for pinholes and do a 2nd prime coat if necessary. If thinning is required, you can add 5% Solvent SLP100™. This applies for the gloss, satin, or matt version.

Discard all leftover Urethane 2Pack™. Do NOT pour unused material from the roller tray back into the original container as this will start the whole material to react and gelling/cure within the drum. Two coats as minimum recommended. Use a lint free epoxy roller to apply the product. The second coat has to be applied within 24 hours of the application of the first coat to ensure the second coat will bite into the first coat. After 24 hours the first coat has to be sanded prior application of the second coat to assure a sound adhesion between coats.

Curing Times

Pot Life: 35-60 minutes, Touch Dry: 1-4 hours, Recoat: 4-24 hours, Full Cure: 7 days.

Allow coating to cure for at least 24 hours before subjecting to light pedestrian traffic and at least 7 days for full cure and vehicular traffic. The pot life time depends on climatic conditions and temperatures. All drying times depend on film thickness, ventilation, temperature, humidity and application methods.

Cleaning

Clean all equipment immediately after use with Solvent SGP80™ or Solvent SLP100™.

Coating Maintenance

In general dirt, dust, contaminants, and excessive wear and tear will shorten the life of coating. Keep these areas clean and free from such pollutants and avoid excessive wear and tear. Clean coating regular with warm mild detergent water up to 60°C and rinse with clean water. Do not use abrasive brushes, scouring pads or solvent to clean the coated surface. It is advisable if abnormal wear and tear will occur through moving furniture such as office chairs, keep these areas protected with a protective mat.

Compatibility & Suitability

Do NOT mix this product or use this product in combination with any other products or brands. Due to the differences in substrates, material and site conditions, and environmental surrounds, the applicator holds whole responsibility for checking the products suitability for its intended purpose prior application. Only products of the same brand/system should be used in combination as a system.

PRECAUTIONS

Safety Data Sheet and Technical Data Sheet must be read before using and opening this product. Keep out of reach of children. Always wear personnel protective equipment (PPE) when handling this product. Keep away from heat and flame. No smoking. Provide adequate ventilation. For more details refer to safety data sheet (SDS).

Do not apply if the air or surface temperature is below 10°C, or if the temperatures is subject to drop below 10°C during applying, or after application within the curing time.

Do not apply if substrate is subject to hydrostatic pressure or rising dampness.

Do not apply if surface is subjected to unusual high temperatures above ambient temperature.

Do not apply if the surface temperature is over 30°C, or if the surface temperature is subject to raise above 30°C during applying, or after application within the curing time, or if relative humidity is suspected to become above 85%.

Do not apply if substrate is subject to rain or moisture, and protect surface at least 24 hours against any water impact, or moisture after application within the curing time. Do not use any product past its pot life. Store locked up, in a cool, dry, well ventilated place, away from sunlight, between 10°C and 30°C. Keep container tightly closed.

DISCLAIMER

Do not apply this product if there is uncertainty about application or surface preparation. This Technical Data Sheet is to be used as a guide only; it is NOT a specification. Durable Concrete Coatings Pty Ltd has no control over the use or storage of this product and therefore does not accept liability in this regard. Any verbal advice given should not be regarded as authoritative information. This information is subject to change without notice, therefore all applicators should ensure they have current information. This product is intended for the use only of skilled tradesman and where applicable, statutory licensed tradesmen experienced and trained in the use of this product. Due to differences in substrates, application methods and local conditions purchasers of these products must ensure that it is suitable for their specific application before using these products. While the information contained in the TDS and SDS is accurate to the best of our knowledge, Durable Concrete Coatings Pty Ltd cannot guarantee that the information contained is wholly comprehensive. Subject to the provisions of the Trade Practices Act, the Company's liability in relation to defective product shall be limited to replacement of the product, proving the product to be defective. Durable Concrete Coatings Pty Ltd all terms and conditions apply.

Durable Concrete Coatings Pty Ltd | 2/100 Kingston Road, Underwood

QLD 4119 Australia

Landline (07) 3808 2769 | Toll Free 1300 800 054

info@durableconcretecoatings.com.au | www.durableconcretecoatings.com.au